

UNVARNISHED OAK COLLECTION

EUROPEAN STANDARD

NORMATIVE EN 13489

- SELECT ●
- NATURE △
- RUSTIC ■
- FREE CLASS
- MIX 1
- MIX 2



Classification for Quercus spp. (Oak)

Face of the element			
FEATURES	●	△	■
Sound sapwood	Not permitted	Permitted up to 50% of the face, if distributed	
Knots*			All features permitted without limit to size or quantity if these do not impair the strength or the wearing quality of the parquet flooring
Sound and intergrown	Permitted if: diameter ≤3 mm if not grouped together**	Permitted if: diameter ≤8 mm	
Unsound knots	Permitted if: diameter ≤1 mm if not grouped together**	Permitted if: diameter <2 mm	
Checks	Not permitted	Permitted up to 20 mm in length per strips	
Bark pockets	Not permitted	Not permitted	
Lightning shake	Not permitted	Not permitted	
Slope of grain	Permitted, no limit	Permitted, no limit	
Colour variation	Slight variation permitted	Permitted	
Medullary ray	Permitted	Permitted	
Biodeterioration	Not permitted	Not permitted	Not permitted, except blue stain and black holes
Non-visible parts			
All features permitted without limit to size or quantity if these do not impair the strength or the wearing quality of the wood flooring.			
* Cracks in knots and knot holes greater than 3 mm shall be filled. ** Knots are grouped together if the distance separating them, measured from edge to edge, does not exceed 30 mm.			