

American Cherry



Stemau



Wood Flooring Production



Specie legnosa: AMERICAN CHERRY



Stemau S.r.l.
Legal Head Office and Showroom Via Pieve Ligure, 15 00168 Rome
Warehouse and Showroom Via Refrancore, 26 00166 Rome
Factory Via Morsasco, 41 00166 Rome
Phone 0039.06.45.50.22.60 - info@stemausr.lit - www.stemausr.lit
VAT 01814361000 - Fiscal Code 07578980588

INFORMATION SHEET In compliance with the provisions of the law Legislative Decree no. 104/2005 "Regulations for consumer information"

EUROPEAN STANDARDS: UNI EN 13227 - UNIKEN 13489
COMMERCIAL NAME: AMERICAN CHERRY
BOTANICAL NAME: PRUNUS SEROTINA
FAMILY: PRUNOIDEAE
ORIGIN: AMERICA
OXIDATION: MEDIUM
HARDNESS: MEDIUM
DENSITY: FRESH 700-850 Kg/m³ - DRY 550-650 Kg/m³
DRYING: EASY AND SLOW TO AVOID TWISTING AND CRACKS
GROWTH AREA: CENTRAL AND SOUTHERN AREAS OF NORTH AMERICA
COLOUR: WARM REDDISH-ORANGE
PROPERTY: MEDIUM HARD WOOD, STABLE AND RESISTANT

SELECT
AMERICAN CHERRY

NATURE
AMERICAN CHERRY

- SELECT**  **UNIFORM TONES, HOMOGENEOUS VEININGS, RANDOM SMALL KNOTS**
- NATURE**  **SLIGHT CHROMATIC SHADES, ACCENTUATED VEININGS, CONTAINED KNOTS**
- RUSTIC**  **MARKED TONE CHANGES, STRONG VEININGS, VISIBLE KNOTS AND CRACKS**



Technical specifications of AMERICAN CHERRY Solid Wood Parquet


ESSENTIAL FEATURES	PERFORMANCE	TECHNICAL SPECIFICATION HARMONIZED
Density kg/m ³	550-650	
Reaction to fire	Dfl-S1	UNI EN 14342-2013 EN 13501-1
Thermal conductivity W/Mk	0,15	UNI EN 14342-2013

QUICK INSTALLATION GUIDE

Laying with glue or nailed (only for planks from thickness of 20 mm and above).

It is recommend using solvent-free glues to avoid stains on the surface.

Installation on underfloor heating: suitable (if the conditions of the system allow for it and comply with the regulations).



Technical specifications of AMERICAN CHERRY 2 or 3 Layers Pre-finished Parquet



ESSENTIAL FEATURES	PERFORMANCE	TECHNICAL SPECIFICATION HARMONIZED
Top layer density kg/m ³	550-650	
Nominal upper layer thickness mm	3/4	
Reaction to fire	Dfl-S1	UNI EN 14342-2013 EN 13501-1
Thermal conductivity W/Mk	0,15	UNI EN 14342-2013

QUICK INSTALLATION GUIDE

2 Layers Laying: with glue or floating (only for planks from width of 120 mm and above).

3 Layers Laying: Floating

It is recommend using solvent-free glues to avoid stains on the surface.

For floating laying, it is recommend using a shock-absorbing or insulating mat.

Installation on underfloor heating: suitable (if the conditions of the system allow for it and comply with the regulations).

