

# Larch Larch



Stemau



Wood Flooring Production





Wood species: LARCH



Wood Flooring Production

Stemau S.r.l.  
Legal Head Office and Showroom Via Pieve Ligure, 15 00168 Rome  
Warehouse and Showroom Via Refrancore, 26 00166 Rome  
Factory Via Morsasco, 41 00166 Rome  
Phone 0039.06.45.50.22.60 - info@stemausr.it - www.stemausr.it  
VAT 01814361000 - Fiscal Code 07578980588

INFORMATION SHEET In compliance with the provisions of the law Legislative Decree no. 206/2005 "Regulations for consumer information"

**EUROPEAN STANDARDS:** UNI EN 13226 - UNI EN 13227 - UNI EN 13489 - UNI EN 11538  
**COMMERCIAL NAME:** LARCH  
**BOTANICAL NAME:** LARIX DECIDUA  
**FAMILY:** PINACEAE  
**ORIGIN:** CENTRAL EUROPE  
**OXIDATION:** LOW  
**HARDNESS:** LOW  
**DENSITY:** FROM 650 TO 750 KG/M<sup>3</sup>  
**DRYING:** SIMPLE AND FAST, IT DOES NOT PRESENT ANY PARTICULAR PROBLEMS  
**GROWTH AREA:** : MOUNTAIN AREAS CENTRAL EUROPE  
**COLOUR:** LIGHT SAPWOOD, HEARTWOOD FROM LIGHT BROWN TO INTENSE RED-BROWN  
**PROPERTY:** WOOD WITH GOOD RESISTANCE AND STABILITY, MEDIUM HARD, EASILY WORKABLE

RUSTIC LARCH



**SELECT** ● **UNIFORM TONES, HOMOGENEOUS VEININGS, RANDOM SMALL KNOTS**  
**NATURE** ▲ **SLIGHT CHROMATIC SHADES, ACCENTUATED VEININGS, CONTAINED KNOTS**  
**RUSTIC** ■ **MARKED TONE CHANGES, STRONG VEININGS, VISIBLE KNOTS AND CRACKS**

# Technical specifications of LARCH Solid Wood Parquet


ESSENTIAL FEATURES	PERFORMANCE	TECHNICAL SPECIFICATION HARMONIZED
Density kg/m <sup>3</sup>	650-750	
Reaction to fire	Dfl-S1	UNI EN 14342-2013 EN 13501-1
Thermal conductivity W/Mk	0,17	UNI EN 14342-2013

## QUICK INSTALLATION GUIDE

Laying with glue or nailed (only for planks from thickness of 20 mm and above).

It is recommend using solvent-free glues to avoid stains on the surface.

Installation on underfloor heating: suitable (if the conditions of the system allow for it and comply with the regulations).



Wood Flooring Production

Stema S.r.l.  
 Legal Head Office and Showroom Via Pieve Ligure, 15 00168 Rome  
 Warehouse and Showroom Via Refrancore, 26 00166 Rome  
 Factory Via Morsasco, 41 00166 Rome  
 Phone 0039.06.45.50.22.60 - info@stemaurl.it - www.stemaurl.it  
 VAT 01814361000 - Fiscal Code 07578980588



# Technical specifications of LARCH 2 or 3 Layers Pre-finished Parquet

ESSENTIAL FEATURES	PERFORMANCE	TECHNICAL SPECIFICATION HARMONIZED
Density kg/m <sup>3</sup>	650-750	
Nominal upper layer thickness mm	3/4	
Reaction to fire	Dfl-S1	UNI EN 14342-2013 EN 13501-1
Thermal conductivity W/Mk	0,17	UNI EN 14342-2013

## QUICK INSTALLATION GUIDE



**2 Layers Laying:** with glue or floating (only for planks from width of 120 mm and above).

**3 Layers Laying:** Floating

*It is recommend using solvent-free glues to avoid stains on the surface.*

*For floating laying, it is recommend using a shock-absorbing or insulating mat.*

**Installation on underfloor heating:** suitable (if the conditions of the system allow for it and comply with the regulations).





# Technical specifications of LARCH for outdoor Decking Parquet

ESSENTIAL FEATURES	PERFORMANCE	TECHNICAL SPECIFICATION HARMONIZED
Density kg/m <sup>3</sup>	650-750	
Reaction to fire	Dfl-S1	UNI EN 14342-2013 EN 13501-1
Thermal conductivity W/Mk	0,17	UNI EN 14342-2013

## QUICK INSTALLATION GUIDE

Installation on aluminum or wooden joists with visible screws for profile **WITHOUT** symmetrical F/F lateral milling or with concealed clips for profile **WITH** symmetrical F/F lateral milling.  
(For installation, in case of slopes, it is necessary to use jacks with adjustable support).

