

European Walnut



Stemau S.p.A.



Wood Flooring Production



Wood species: EUROPEAN WALNUT



Wood Flooring Production

Stema S.r.l.

Legal Head Office and Showroom Via Pieve Ligure, 15 00168 Rome
 Warehouse and Showroom Via Refrancore, 26 00166 Rome
 Factory Via Morsasco, 41 00166 Rome
 Phone 0039.06.45.50.22.60 - info@stemausr.it - www.stemausr.it
 VAT 01814361000 - Fiscal Code 07578980588

INFORMATION SHEET In compliance with the provisions of the law Legislative Decree no. 206/2005 "Regulations for consumer information"

EUROPEAN STANDARDS: UNI EN 13226 - UNI EN 13227 - UNI EN 13489

COMMERCIAL NAME: EUROPEAN WALNUT

BOTANICAL NAME: JUGLANS REGIA

FAMILY: JUGLANDACEAE

ORIGIN: EUROPE

OXIDATION: LOW

HARDNESS: HIGH

DENSITY: 550-650 KG/M³

DRYING: EASY AND GOOD

GROWTH AREA: EUROPE

COLOUR: WHITEISH SAPPHEN AND BROWN-GREY HARDWOOD WITH DARK SHADES AND VEINS

PROPERTY: RESISTANT, STABLE, PRECIOUS AND REFINED WOOD, MUCH APPRECIATED FOR THE CHARACTERISTICS OF ITS TYPICAL GRAINS

SELECT EUROPEAN WALNUT



NATURE EUROPEAN WALNUT



RUSTIC EUROPEAN WALNUT



- SELECT**  **UNIFORM TONES, HOMOGENEOUS VEININGS, RANDOM SMALL KNOTS**
- NATURE**  **SLIGHT CHROMATIC SHADES, ACCENTUATED VEININGS, CONTAINED KNOTS**
- RUSTIC**  **MARKED TONE CHANGES, STRONG VEININGS, VISIBLE KNOTS AND CRACKS**

Technical specifications of EUROPEAN WALNUT Solid Wood Parquet

ESSENTIAL FEATURES	PERFORMANCE	TECHNICAL SPECIFICATION HARMONIZED
Density kg/m ³	550-650	
Reaction to fire	Dfl-S1	UNI EN 14342-2013 EN 13501-1
Thermal conductivity W/Mk	0,17	UNI EN 14342-2013

QUICK INSTALLATION GUIDE

Laying with glue or nailed (only for planks from thickness of 20 mm and above).

It is recommend using solvent-free glues to avoid stains on the surface.

Installation on underfloor heating: suitable (if the conditions of the system allow for it and comply with the regulations).



Technical specifications of EUROPEAN WALNUT 2 or 3 Layers Pre-finished Parquet



ESSENTIAL FEATURES	PERFORMANCE	TECHNICAL SPECIFICATION HARMONIZED
Density kg/m ³	550-650	
Nominal upper layer thickness mm	3/4	
Reaction to fire	Dfl-S1	UNI EN 14342-2013 EN 13501-1
Thermal conductivity W/Mk	0,17	UNI EN 14342-2013

QUICK INSTALLATION GUIDE

2 Layers Laying: with glue or floating (only for planks from width of 120 mm and above).

3 Layers Laying: Floating

It is recommend using solvent-free glues to avoid stains on the surface.

For floating laying, it is recommend using a shock-absorbing or insulating mat.

Installation on underfloor heating: suitable (if the conditions of the system allow for it and comply with the regulations).

