

Olive



N  
E  
M  
A



Stemau S.p.A.



Wood Flooring Production





Wood species: OLIVE



Wood Flooring Production

Stemau S.r.l.

Legal Head Office and Showroom Via Pieve Ligure, 15 00168 Rome  
Warehouse and Showroom Via Refrancore, 26 00166 Rome  
Factory Via Morsasco, 41 00166 Rome  
Phone 0039.06.45.50.22.60 - info@stemausr.lit - www.stemausr.lit  
VAT 01814361000 - Fiscal Code 07578980588

INFORMATION SHEET In compliance with the provisions of the law Legislative Decree no. 206/2005 "Regulations for consumer information"

**EUROPEAN STANDARDS: UNI EN 13226 - UNEN 13227**

**COMMERCIAL NAME: OLIVE**

**BOTANICAL NAME: OLEA EUROPAEA**

**FAMILY: OLEACEAE**

**ORIGIN: EUROPE**

**OXIDATION: LOW**

**HARDNESS: VERY HIGH**

**DENSITY: FROM 1050 TO 1150 KG/M<sup>3</sup>**

**DRYING: VERY SLOW TO AVOID SPLITS AND CRACKS**

**GROWTH AREA: ITALY**

**COLOUR: DARK BROWN-YELLOW WITH LIGHTER STREAKS**

**PROPERTY: PARTICULARLY HARD WOOD, VERY RESISTANT, WITH DENSE GRAIN AND IRREGULAR MOVEMENTS, DIFFICULT TO WORK**

SELECT OLIVE



NATURE OLIVE



- SELECT**  **UNIFORM TONES, HOMOGENEOUS VEININGS, RANDOM SMALL KNOTS**
- NATURE**  **SLIGHT CHROMATIC SHADES, ACCENTUATED VEININGS, CONTAINED KNOTS**
- RUSTIC**  **MARKED TONE CHANGES, STRONG VEININGS, VISIBLE KNOTS AND CRACKS**



# Technical specifications of OLIVE Solid Wood Parquet

ESSENTIAL FEATURES	PERFORMANCE	TECHNICAL SPECIFICATION HARMONIZED
Density kg/m <sup>3</sup>	1050-1150	
Reaction to fire	Dfl-S1	UNI EN 14342-2013 EN 13501-1
Thermal conductivity W/Mk	0,21	UNI EN 14342-2013

## QUICK INSTALLATION GUIDE

Laying with glue or nailed (only for planks from thickness of 20 mm and above).

It is recommend using solvent-free glues to avoid stains on the surface.

Installation on underfloor heating: suitable (if the conditions of the system allow for it and comply with the regulations).

